

Slip Check to AS 4586-2013 Floor Graphic Lamination Matte

Report Number: R21369b

Report Date: 7 July 2020

Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

Issued by

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

[REDACTED]
[REDACTED]
[REDACTED]

Approved by



Nasser Cura
Authorised Signatory

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd

7 July 2020

Test Report No. R21369b

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: [REDACTED]
 Client Address: [REDACTED]
 Product Manufacturer: [REDACTED]
 Product Description: Floor Graphic Lamination Matte

Test conducted according to: AS 4586:2013 Appendix A
 Location: 4/40 Bessemer Street, Blacktown NSW 2148
 Conducted by: Yuliana Vargolomova

Date:	7 July 2020	Temperature:	16°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	NA		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	47	41	47	47	49

Reported SRV of Sample:	46
Class:	P4

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd